

TEST CONDUCTED

TEST RESULT

(01) FLAMMABILITY (FAA PART 25 APP. F PART I (b)(4) 12 SECOND VERTICAL TEST -
 CITATION : 25.853(a) & APPENDIX F PART I (a)(1)(ii))

#1

AS RECIEVED	
AFTER FLAME TIME(s)	
- WARP	0 0 0 // 0
- WEFT	0 0 0 // 0
DRIP BURN(s)	
- WARP	0 0 0 // 0
- WEFT	0 0 0 // 0
CHAR LENGTH(mm)	
- WARP	157 151 155 // 154
- WEFT	141 152 138 // 144

NOTE) CONCLUSION : BASED UPON THE RESULTS OF THE REPORT FOR THE SUBMITTED SAMPLE MEETS
 PERFORMANCE REQUIREMENTS AS STATED IN FAA 25.853(a) &
 APPENDIX F PART I (a)(1)(ii).

ACCEPTANCE CRITERIA : AFTER FLAME TIME (s) : Avg. 15
 DRIP BURN (s) : Avg. 5
 CHAR LENGTH (mm) : Avg. 203

TEST WAS CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENT'S REQUEST.

(02) FLAMMABILITY (NFPA 701 SMALL SCALE TEST:1989)

#1

LENGTH	
AFTER FLAME TIME(s)	0 0 0 0 0
DRIP BURN(s)	0 0 0 0 0
DAMAGED LENGTH(mm)	137 142 139 144 147
WIDTH	
AFTER FLAME TIME(s)	0 0 0 0 0
DRIP BURN(s)	0 0 0 0 0
DAMAGED LENGTH(mm)	118 121 119 128 124

NOTE) CONCLUSION : BASED UPON THE RESULTS OF THE TEST REPORT FOR THE SUBMITTED SAMPLE
 MEETS THE PERFORMANCE REQUIREMENTS AS STATED IN NFPA 701, SMALL SCALE TEST.

ACCEPTANCE CRITERIA : CURTAINS AND DRAPERIES

FABRIC WEIGHT (oz/yd ²)	: LESS THAN 10	
AFTER FLAME TIME(s)	: Max.Avg. NOT SPECIFIED	Max. Ind. NOT SPECIFIED
DRIP BURN(s)	: Max.Avg. 2.0	Max. Ind. NOT SPECIFIED
CHAR LENGTH(mm)	: Max.Avg. 165	Max. Ind. 191

TEST REPORT

APPLICANT : CLEANBRANDS

REPORT NO. : K214-08-16212

SAMPLE RECEIVED DATE : 2008-10-13

TEST STARTED DATE : 2008-10-13

REPORT ISSUED DATE : 2008-10-17

PAGE : 1 OF 2

SAMPLE DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE WOVEN FABRIC.

=====

ITEM : M14000
COLOR NAME : WHITE

=====


TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

=====

PREPARED AND CHECKED BY
FOR FITI


SANG SOO, HAN
QUALITY MANAGER

AUTHORIZED BY
FOR FITI


WOO-JUNG SHIM
EXECUTIVE DIRECTOR